

Product Information

Vipel® Vinyl Ester Based Resin for Underground Sewer Pipe Liners



TYPICAL LIQUID RESIN PROPERTIES *(1) Vipel®L010-PPA-38 see back

	Nominal
Viscosity @ 77°F/25°C, RVF Brookfield Spindle #4 @ 20 RPM, cps.	5000
Thix Index 2/20	4.3
Color	Opaque
Specific Gravity @ 77°F/25°C	1.07
Non-Volatiles, %	58
Gel Time @ 140°F with (1.0% Di-(4-tert-butyl-cyclohexyl) peroxydicarbonate and 0.5% tert-butyl peroxybenzoate, minutes	25
Pot Life @ 77°F/25°C (1% Di-(4-tert-butyl-cyclohexyl) peroxydicarbonate and + 0.5% tert-butyl peroxybenzoate, hours	20

DESCRIPTION

The Vipel L010-PPA series is a bisphenol-A epoxy-based resin vinyl ester resin dissolved in styrene. AOC's Vipel® L010-PPA Series provides the corrosion resistance, durability and toughness that is required for cured in place pipe applications. Refer to the AOC Corrosion Resistant Resin Guide for corrosion resistance information listed under Vipel® F010.

FEATURES

- Excellent catalyzed pot life
- Superior mechanical properties

BENEFITS

Adaptability

AOC's Vipel L010-PPA Series molecular architecture provides an excellent balance of corrosion and physical properties.

TYPICAL CAST MECHANICAL PROPERTIES* (2) see back page

		Test Method
Tensile Strength,psi/MPa	13,800/95	ASTM D 638
Tensile Modulus,psi/GPa	540,000/3.7	ASTM D 638
Tensile Elongation, %	4.6	ASTM D 638
Flexural Strength,psi/MPa	22,000/151	ASTM D 790
Flexural Modulus,psi/GPa	570,000/3.9	ASTM D 790
Heat Distortion Temperature, °F/°C @ 264 psi	234/112	ASTM D 648
Barcol Hardness	>40	ASTM D 2583

*Typical properties are not to be construed as specifications.

Vipel® L010-PPA Series Vinyl Ester Resin

PERFORMANCE GUIDELINES

A. Keep full strength catalyst levels between 1.0% - 3.0% of the total resin weight.

B. Maintaining shop temperatures between 65°F/ 18°C and 90°F/32°C and humidity between 40% and 90% will help the fabricator make a high quality part. Consistent shop conditions contribute to consistent gel times.

STORAGE STABILITY

Resins are stable for six months from date of production when stored in the original containers away from sunlight at no more than 70°F/21°C. After extended storage, some drift may occur in gel time.

During the hot summer months, no more than two months stability at 86°F/30°C should be anticipated.

SAFETY

See appropriate Material Safety Data Sheet for guidelines.

ISO 9001:2000 CERTIFIED

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2000 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

FOOTNOTES

(1)

The gel times shown are typical but may be affected by catalyst, promoter and inhibitor concentrations and resin, mold and shop temperature. Variations in gelling characteristics can be expected between different lots of catalysts and at extremely high humidities. Pigment and fillers can retard or accelerate gelation. It is recommended that the fabricator check the gelling characteristics of a small quantity of resin under actual operating conditions prior to use.

(2)

Based on tests of Vipel® F010-CNT-17 at 73°F/ 23°C and 50% relative humidity. All thixotropic resins should be mixed well prior to use. The use of thixotropy degrades the corrosion performance of a resin in some chemical environments such as sodium chloride. All tests on unreinforced cured resin. Castings prepared using 1.0% MEKP, .08% Cobalt 6% post cured 10 hours at 212°F/100°C using AOC test method X-12Ab.

The information contained in this data sheet is based on laboratory data and field experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability for occurrences arising out of its use. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing each such product before committing to production.

Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code or insurance regulation.

www.aoc-resins.com



North America
northamerica@aoc-resins.com
Toll Free: +1 (866) 319-8827
+1 901-854-7277 Fax

Africa
africa@aoc-resins.com
+44 1473 288997
+44 1473 216080 Fax

Asia
asia@aoc-resins.com
+44 1473 288997
+44 1473 216080 Fax

Australia
australia@aoc-resins.com
+44 1473 288997
+44 1473 216080 Fax

Europe
europe@aoc-resins.com
+44 1473 288997
+44 1473 216080 Fax

Latin America
latinamerica@aoc-resins.com
+01 863 815 5016
+01 863 815 4733 Fax

Middle East
middleeast@aoc-resins.com
+44 1473 288997
+44 1473 216080 Fax