

Product Information

Vipel® Isophthalic Based Resin for Underground Sewer Pipe Liners

TYPICAL LIQUID RESIN PROPERTIES*(1) Vipel®L704-AAP-12 see back page

	Nominal
Viscosity @ 77°F/25°C, RVF Brookfield (with ATH-filler)	
Spindle #4 @ 20 RPM, cps.	6,200
Thix Index 2/20	3.5 Min
Color	Opaque
Specific Gravity @ 77°F/25°C	1.26 Neat
Styrene %	40
Gel Time @ 140°F with (1.0% Di-(4-tert-butyl-cyclohexyl) peroxydicarbonate and 0.5% Trigonox® KSM), minutes	10
Pot Life @ 77°F/25°C (1% Di-(4-tert-butyl-cyclohexyl) peroxydicarbonate and + 0.5% Trigonox® KSM), hours	24+

Trigonox is a trademark of Akzo Nobel Chemicals

TYPICAL CAST MECHANICAL PROPERTIES* (2) see back page

		Test Method
Tensile Strength, psi/MPa	8,000/58	ASTM D 638
Tensile Modulus, psi/GPa	730,000/5.0	ASTM D 638
Tensile Elongation, %	2	ASTM D 638
Flexural Strength, psi/MPa	12,000/83	ASTM D 790
Flexural Modulus, psi/GPa	750,000/5.2	ASTM D 790
Heat Distortion Temperature, °F/°C @ 264 psi	207/97	ASTM D 648
Barcol Hardness	40	ASTM D 2583

*Typical properties are not to be construed as specifications.



DESCRIPTION

The Vipel® L704-FAP Series is a high molecular weight isophthalic/unsaturated polyester resin enhanced with ATH. Vipel® L704-FAP Series provides the corrosion resistance, durability and toughness that is required for cured in place pipe applications.

FEATURES

- Excellent catalyzed pot life
- Superior mechanical properties
- High molecular weight
- High viscosity version

Vipel® L704-FAP Series Polyester Resin

PERFORMANCE GUIDELINES

A. Keep full strength catalyst levels between 1.0% - 3.0% of the total resin weight.

B. Maintaining shop temperatures between 65°F/ 18°C and 90°F/32°C and humidity between 40% and 90% will help the fabricator make a high quality part. Consistent shop conditions contribute to consistent gel times.

STORAGE STABILITY

Resins are stable for six months from date of production when stored in the original containers away from sunlight at no more than 70°F/21°C. After extended storage, some drift may occur in gel time.

During the hot summer months, no more than two months stability at 86°F/30°C should be anticipated.

SAFETY

See appropriate Material Safety Data Sheet for guidelines.

ISO 9001:2000 CERTIFIED

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2000 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

FOOTNOTES

(1)

The pot life times shown are typical but may be affected by catalyst, promoter and inhibitor concentrations in resin, and environmental temperature. Variations in gelling characteristics can be expected between different lots of catalysts and at extremely high humidities. Pigment and fillers can retard or accelerate gelation. It is recommended that the fabricator check the gelling characteristics of a small quantity of resin under actual operating conditions prior to use.

(2)

Based on tests on Vipel® L704-FAP pipe at 77°F/25° and 50% relative humidity. Castings were prepared using 1.0% Perkadox 16 and 0.5 Trigonox C.

The information contained in this data sheet is based on laboratory data and field experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability for occurrences arising out of its use. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing each such product before committing to production.

Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code or insurance regulation.



950 HIGHWAY 57 EAST
COLLIERVILLE, TN 38017
www.aoc-resins.com

NORTH AMERICA

Tel: 001(901) 854-2800
Fax: 001 (901) 854-7277
sales@aoc-resins.com

ASIA, MIDDLE EAST & LATIN AMERICA

Tel: 001 (863) 815-5016
Fax: 001 (863) 815-4733
international@aoc-resins.com

EUROPE

Tel: (44) 1473 288997
Fax: (44) 1473 216080
europe@aoc-resins.com